



Central Plains Cement Company

Cement Mill Test Report

Month of Issue: August 2018

Plant: Tulsa, OK
Product: Masonary Cement Type N
Silo: 7
Manufactured: July 2018

ASTM C 91-12 Standard Requirements

Item	Spec limit	Test Result
Fineness, Residue retained on a 45 um sieve (%)	24 max	10
Time of setting, Gillmore method: Initial set, minutes	120 min 1000 max	240
Compressive strength (MPa, PSI) 7 days 28 days (Reflects previous month's data)	500 min 900 min	720 1150
Air content of mortar (%)	8 min 21 max	18
Water Retention (% of original flow)	70 min	82

We certify that the above described cement, at the time of shipment, meets the requirements of ASTM C 91-12.

Certified By:

John Tierney

August 7, 2018

Central Plains Cement Co. LLC - Tulsa Plant
2609 North 145th East Ave
Tulsa, OK 74012
918-437-3902